

**TEST REPORT****NUMBER : VNMT11003285****DATE : 10-Mar-2011**APPLICANT : **K.V COLLECTION INC.**

3217 S. GARFIELD AVE., COMMERCE, CA 90040, UNITED STATES OF AMERICA..


Sample Description As Declared : One (1) Piece Of Submitted Knit Fabric Sample Said To Be French Terry In White Color.  
Fiber Content : 60% Cotton 40% Polyester  
Colour : White  
Style No. :  
Order No./PO No. :  
Fabric Weight: : 240 G/M<sup>2</sup>

---

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

---

PREPARED & CHECKED BY :  
FOR INTERTEK VIETNAM LTD. [VIETNAM]



THANH NGUYEN  
OPERATIONS MANAGER

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

**Intertek Vietnam Ltd.**

Page 1 of 5

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

**1. Wearing Apparel Flammability Test.**

US CPSC 16 CFR 1610 2008

Face

Plain Surface       Raised Surface

BURN DIRECTION <input checked="" type="checkbox"/> Length			BURN DIRECTION <input checked="" type="checkbox"/> Length		
Preliminary			Preliminary		
	Burn code	Time in Sec		Burn code	Time in sec
Face 1	DNI		Face 1	DNI	
Face 2	DNI		Face 2	DNI	
Back 1	DNI		Back 1	DNI	
Back 2	DNI		Back 2	DNI	
<b>Original</b>			<b>After One Drycleaning / Laundering</b>		
1	DNI		1	DNI	
2	DNI		2	DNI	
3	DNI		3	DNI	
4	DNI		4	DNI	
5	DNI		5	DNI	
6	DNI		6	DNI	
7	DNI		7	DNI	
8	DNI		8	DNI	
9	DNI		9	DNI	
10	DNI		10	DNI	

Classification :  Class 1, Normal Flammability

Requirement : Class 1

## Classification:

- [x] Class 1, Normal Flammability  
[ ] Class 2, Intermediate Flammability, Raised Surface  
[ ] Class 3, Rapid and Intense Burning

Dryclean/Washing Instruction: Follow Commercial Drycleaning/ Washing  
Condition: 12 Minutes Machine Wash At 120°F, Normal Cycle, Followed By Tumble  
Dry Medium.

## Explanation of Flammability Results:

BB: Base Burn

\*IBE: Ignited, but extinguished, the asterisk (\*) denotes a burn that goes under the cord without breaking the cord.

DNI: Did not ignite

IBE: Ignited but extinguished

\*0.0 SFBB poi: Time in seconds, surface flash base burn possibly starting at the point of impingement. The asterisk is accompanied by the following  
''Unable to make absolute determination as to source of base burns.''

This note is added to the result of any specimen if there is a question as to origin of the base burning.

It does not qualify as a base burn under the current interpretation of CFR 1610.

0.0 SF only: Time in seconds, surface flash only. No damage to the base fabric.

SF pw: Surface flash, part way.

No time shown because the surface flash did not reach the cord.

SF uc: Surface flash, under the cord, but does not break the cord.

SF poi: Surface flash, at point of impingement only (equivalent to ''did not ignite'' for plain surface)

---

## END OF THE TEST REPORT ##