

TEST REPORT

NUMBER : VNMT08009438

DATE : 24-Dec-2008

APPLICANT : K.V. COLLECTIONS INC.

6832 EAST SLAUSON AVE COMMERCE, CA
90040, United States Of America, -

ATTN : MS.TUYEN.

Sample Description : Four (4) Pieces Of Submitted Knit Fabric
Samples Said To Be 100% Combed Cotton 2x1 Rib
In Colors :
(A) Hot Pink
(B) Lime
(C) Red
(D) Butter

Fabric Weight : 215 g/m²
Fiber Content : 100% Cotton
Style No : -
Order No. : -
Color : (A)Hot Pink , (B)Lime , (C)Red , (D)Butter
Date Received/Date Test Started : 19-Dec-2008

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

NOTE :

Based Upon The Results Of The Flammability Test Reported,
The Sample Submitted For Testing Is Rated As A Class 1
Material (Normal Flammability) When Tested And Classified In
Accordance With Procedures And Requirements Of The Federal
Flammable Fabrics Act Of 16 CFR Part 1610 Originally
Effective From January 1953.

PREPARED & CHECKED BY :
FOR INTERTEK LABTEST [VIETNAM]



IN HUAT
OPERATION MANAGER

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Testing Services Vietnam Ltd.

Page 1 of 6

Hanoi office: B11 4th Floor, Hanoi Horizon Hotel Building, 40 Cat Linh Street, Dong Da District, Hanoi.

Tel : (84-4) 37337094 Fax : (84-4) 37337093 Website : www.intertek-labtest.com

Hochiminh office: 1st Floor, E.Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.

Tel : (84-8) 62971099 Fax : (84-8) 62971098 Email : labtest.vietnam@intertek.com

Handwritten mark

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Wearing Flammability

16 CFR 1610 - 2008

(A)

Plain Surface Raised Surface

BURN DIRECTION <input checked="" type="checkbox"/> Length			BURN DIRECTION <input checked="" type="checkbox"/> Length		
Preliminary			Preliminary		
Length	Burn code	Time in Sec	Width	Burn code	Time in sec
Face1	DNI		Face1	DNI	
Face2	DNI		Face2	DNI	
Back1	DNI		Back1	DNI	
Back2	DNI		Back2	DNI	
Original			After One Dry Cleaning / Laundering		
1 DNI			1 DNI		
2 DNI			2 DNI		
3 DNI			3 DNI		
4 DNI			4 DNI		
5 DNI			5 DNI		
6 DNI			6 DNI		
7 DNI			7 DNI		
8 DNI			8 DNI		
9 DNI			9 DNI		
10 DNI			10 DNI		

Classification : Class 1, Normal Flammability

(B)

Plain Surface Raised Surface

BURN DIRECTION <input checked="" type="checkbox"/> Length			BURN DIRECTION <input checked="" type="checkbox"/> Length		
Preliminary			Preliminary		
Length	Burn code	Time in Sec	Width	Burn code	Time in sec
Face1	DNI		Face1	DNI	
Face2	DNI		Face2	DNI	
Back1	DNI		Back1	DNI	
Back2	DNI		Back2	DNI	
Original			After One Dry Cleaning / Laundering		
1	DNI		1	DNI	
2	DNI		2	DNI	
3	DNI		3	DNI	
4	DNI		4	DNI	
5	DNI		5	DNI	
6	DNI		6	DNI	
7	DNI		7	DNI	
8	DNI		8	DNI	
9	DNI		9	DNI	
10	DNI		10	DNI	

Classification : Class 1, Normal Flammability

(c)

Plain Surface Raised Surface

BURN DIRECTION <input checked="" type="checkbox"/> Length			BURN DIRECTION <input checked="" type="checkbox"/> Length		
Preliminary			Preliminary		
Length	Burn code	Time in Sec	Width	Burn code	Time in sec
Face1	DNI		Face1	DNI	
Face2	DNI		Face2	DNI	
Back1	DNI		Back1	DNI	
Back2	DNI		Back2	DNI	
Original			After One Dry Cleaning / Laundering		
1 DNI			1 DNI		
2 DNI			2 DNI		
3 DNI			3 DNI		
4 DNI			4 DNI		
5 DNI			5 DNI		
6 DNI			6 DNI		
7 DNI			7 DNI		
8 DNI			8 DNI		
9 DNI			9 DNI		
10 DNI			10 DNI		

Classification : Class 1, Normal Flammability

(D)

Plain Surface Raised Surface

BURN DIRECTION <input checked="" type="checkbox"/> Length			BURN DIRECTION <input checked="" type="checkbox"/> Length		
Preliminary			Preliminary		
Length	Burn code	Time in Sec	Width	Burn code	Time in sec
Face1	DNI		Face1	DNI	
Face2	DNI		Face2	DNI	
Back1	DNI		Back1	DNI	
Back2	DNI		Back2	DNI	
Original			After One Dry Cleaning / Laundering		
1 DNI			1 DNI		
2 DNI			2 DNI		
3 DNI			3 DNI		
4 DNI			4 DNI		
5 DNI			5 DNI		
6 DNI			6 DNI		
7 DNI			7 DNI		
8 DNI			8 DNI		
9 DNI			9 DNI		
10 DNI			10 DNI		

Classification : Class 1, Normal Flammability

TEST REPORT

NUMBER : VNMT08009438

DATE : 24-Dec-2008

REMARK :

Classification:

- Class 1, Normal Flammability
 Class 2, Intermediate Flammability, Raised Surface
 Class 3, Rapid and Intense Burning

Drycleaning Procedure Follow Commercial Drycleaning.

Explanation of Flammability Results:

BB: Base Burn

IBE: Ignited, but extinguished, the asterisk () denotes a burn that goes under the cord without breaking the cord.

DNI: Did not ignite

IBE: Ignited but extinguished

*0.0 SFBB poi: Time in seconds, surface flash base burn possibly starting at the point of impingement. The asterisk is accompanied by the following

''Unable to make absolute determination as to source of base burns.''

This note is added to the result of any specimen if there is a question as to origin of the base burning.

It does not qualify as a base burn under the current interpretation of CFR 1610.

0.0 SF only: Time in seconds, surface flash only. No damage to the base fabric.

0.0 SFBB: Time in seconds, surface flash base burn.

Base starts burning at points other than that point of impingement.

0.0 SFBB poi: Time in seconds, surface flash base burn starting at the point of impingement.

SF pw: Surface flash, part way.

No time shown because the surface flash did not reach the cord.

SF uc: Surface flash, under the cord, but does not break the cord.

SF poi: Surface flash, at point of impingement only (equivalent to ''did not ignite'' for plain surface)

END OF THE TEST REPORT