

TEST REPORT

NUMBER : VNMT09011177

DATE : 21-Dec-2009

APPLICANT : K.V. COLLECTIONS INC.

6832 EAST SLAUSON AVE COMMERCE, CA
90040, United States Of America-

ATTN : MS.TUYEN.

Sample Description : One (1) Piece Of Submitted Fabric Sample Said
To Be Burn Out 60% Cotton 40% Polyester In
Charcoal Color

Exported To : USA

Fiber Content : 60% Cotton 40% Polyester

Order No. : -

Style No. :

Color : Charcoal


Fabric Weight: : 140g/m2

Country Of Original : Vietnam

Date Received : 16-Dec-2009

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE
REFER TO ENCLOSED PAGE(S)

Prepared & Checked By :
For INTERTEK VIETNAM LTD. [Vietnam]



Simon Mak
Ph. D [General Manager]

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT
WRITTEN APPROVAL FROM THE LABORATORY)

Page 1 of 3

Intertek Vietnam Ltd.

Hanoi office: D11 4th Floor, Hanoi Horizon Hotel Building, 40 Cat Linh Street, Dong Da District, Hanoi.

Tel: (84-4) 37337034 Fax: (84-4) 37337093 Website: www.intertek-labtest.com

Ho Chi Minh office: 1st Floor, E-Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.

Tel: (84-0) 62971099 Fax: (84-0) 62971098 Email: labtest.vietnam@intertek.com

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Wearing Apparel Flammability

US CPSC 16 CFR Part 1610 - 2008

Plain Surface Raised Surface

BURN DIRECTION <input checked="" type="checkbox"/> Length			BURN DIRECTION <input checked="" type="checkbox"/> Length		
Preliminary			Preliminary		
	Burn code	Time in Sec		Burn code	Time in sec
Face 1	BB	14.4	Face 1	BB	11.5
Face 2	BB	10.6	Face 2	BB	7.2
Back 1	BB	8.5	Back 1	BB	7.6
Back 2	BB	10.9	Back 2	BB	7.8
Original			After One Drycleaning / Laundering		
1	8.5 BB		1	7.2 BB	
2	8.9 BB		2	7.0 BB	
3	8.3 BB		3	6.9 BB	
4	9.0 BB		4	7.3 BB	
5	8.6 BB		5	7.5 BB	
Average 8.7 BB			Average 7.2 BB		

Classification : Class 1, Normal Flammability

Requirement : -

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Classification:

- Class 1, Normal Flammability
 Class 2, Intermediate Flammability, Raised Surface
 Class 3, Rapid and Intense Burning

Dryclean/Washing Instruction: Follow Commercial Drycleaning/ Washing
Condition: 12 Minutes Machine Wash At 120°F, Normal Cycle, Followed By Tumble
Dry Medium.

Explanation of Flammability Results:

BB: Base Burn

IBE: Ignited, but extinguished, the asterisk () denotes a burn that goes under the cord without breaking the cord.

DNI: Did not ignite

IBE: Ignited but extinguished

*0.0 SFBB poi: Time in seconds, surface flash base burn possibly starting at the point of impingement. The asterisk is accompanied by the following
''Unable to make absolute determination as to source of base burns.''

This note is added to the result of any specimen if there is a question as to origin of the base burning.

It does not qualify as a base burn under the current interpretation of CFR 1610.

0.0 SF only: Time in seconds, surface flash only. No damage to the base fabric.

SF pw: Surface flash, part way.

No time shown because the surface flash did not reach the cord.

SF uc: Surface flash, under the cord, but does not break the cord.

SF poi: Surface flash, at point of impingement only (equivalent to ''did not ignite'' for plain surface)

END OF THE TEST REPORT

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Page 3 of 3

Intertek Vietnam Ltd.

Hanoi office: B11 4th Floor, Hanoi Horizon Hotel Building, 40 Cat Linh Street, Dong Da District, Hanoi.

Tel : (84-4) 37337094 Fax : (84-4) 37337093 Website : www.interteklabtest.com

Hochiminh office: 1st Floor, E Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.

Tel : (84-8) 62971099 Fax : (84-8) 62971098 Email : labtest.vietnam@intertek.com