

APPLICANT : K.V. COLLECTIONS INC.

6832 EAST SLAUSON AVE COMMERCE, CA  
90040, United States Of America-

ATTN : MS.TUYEN.

Sample Description : One (1) Piece Of Submitted Fabric Sample Said  
To Be **Single Jersey 100% Cotton** In Brown Color

Exported To : USA

Fiber Content : 100% Cotton

Order No. : -

Style No. : -

Color : Brown

Fabric Weight: : 140g/m2

Country Of Original : Vietnam


Date Received : 16 Dec 2009

---

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE  
REFER TO ENCLOSED PAGE(S)

---

Prepared & Checked By :  
For INTERTEK VIETNAM LTD. [Vietnam]



Simon Mak  
Ph. D [General Manager]

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT  
WRITTEN APPROVAL FROM THE LABORATORY)

Page 1 of 3

**Intertek Vietnam Ltd.**

Hanoi office: B11 4th Floor, Hanoi Horizon Hotel Building, 40 Cat Linh Street, Dong Da District, Hanoi.

Tel : (84-4) 37337094 Fax : (84-4) 37337093 Website : [www.intertek-labtest.com](http://www.intertek-labtest.com)

Hochiminh office: 1st Floor, E.Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.

Tel : (84-8) 62971099 Fax : (84-8) 62971098 Email : [labtest.vietnam@intertek.com](mailto:labtest.vietnam@intertek.com)

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

**1. Wearing Apparel Flammability**

US CPSC 16 CFR Part 1610 - 2008

Plain Surface       Raised Surface

BURN DIRECTION <input checked="" type="checkbox"/> Length			BURN DIRECTION <input checked="" type="checkbox"/> Length		
Preliminary			Preliminary		
	Burn code	Time in Sec		Burn code	Time in sec
Face 1	DNI		Face 1	DNI	
Face 2	DNI		Face 2	DNI	
Back 1	DNI		Back 1	DNI	
Back 2	DNI		Back 2	DNI	
Original			After One Drycleaning / Laundering		
1	DNI		1	DNI	
2	DNI		2	DNI	
3	DNI		3	DNI	
4	DNI		4	DNI	
5	DNI		5	DNI	
6	DNI		6	DNI	
7	DNI		7	DNI	
8	DNI		8	DNI	
9	DNI		9	DNI	
10	DNI		10	DNI	

Classification :  Class 1, Normal Flammability

Requirement :

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

## Classification:

- Class 1, Normal Flammability  
 Class 2, Intermediate Flammability, Raised Surface  
 Class 3, Rapid and Intense Burning

Dryclean/Washing Instruction: Follow Commercial Drycleaning/ Washing  
Condition: 12 Minutes Machine Wash At 120°F, Normal Cycle, Followed By Tumble  
Dry Medium.

## Explanation of Flammability Results:

BB: Base Burn

\*IBE: Ignited, but extinguished, the asterisk (\*) denotes a burn that goes  
under the cord without breaking the cord.

DNI: Did not ignite

IBE: Ignited but extinguished

\*0.0 SFBB poi: Time in seconds, surface flash base burn possibly starting at  
the point of impingement. The asterisk is accompanied by the following  
''Unable to make absolute determination as to source of base burns.''

This note is added to the result of any specimen if there is a question as to  
origin of the base burning.

It does not qualify as a base burn under the current interpretation of CFR  
1610.

0.0 SF only: Time in seconds, surface flash only. No damage to the base  
fabric.

SF pw: Surface flash, part way.

No time shown because the surface flash did not reach the cord.

SF uc: Surface flash, under the cord, but does not break the cord.

SF poi: Surface flash, at point of impingement only (equivalent to ''did not  
ignite'' for plain surface)

---

## END OF THE TEST REPORT ##

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT  
WRITTEN APPROVAL FROM THE LABORATORY)

Page 3 of 3

**Intertek Vietnam Ltd.**

Hanoi office: B11 4th Floor, Hanoi Horizon Hotel Building, 40 Cat Linh Street, Dong Da District, Hanoi.

Tel: (84-4) 37337094 Fax: (84-4) 37337093 Website: www.interteklabtest.com

Hochiminh office: 1st Floor, E.Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.

Tel: (84-8) 62971099 Fax: (84-8) 62971098 Email: labtest.vietnam@intertek.com